

## COROFLOOR EP High Performance Epoxy Resin Flooring

### PRODUCT DESCRIPTION

**COROFLOOR EP** is a high performance, chemical resistant flooring system based on 100% solids Epoxy resin.

### FLOORING LAYERS COMPOSITION

This two component resin system can be applied as a standalone coating, a broadcast or slurry broadcast flooring, and as a heavy-duty trowel applied floor topping.

### FIELDS OF APPLICATION

**COROFLOOR EP** has very good chemical resistance to a wide range of alkalis, salts and many mild inorganic and organic acids. It is used for the protection of concrete floors in chemical process and storage areas, truck loading/unloading areas, secondary containment and high traffic areas in a wide range of industries where chemical processes are present.

### FEATURES

- Versatile design (multi-purpose applications)
- Easy to apply
- Good chemical resistance
- Locally sourced aggregate can be used
- Solvent free, low odor

### CHEMICAL RESISTANCE

Information on the chemical resistance properties is available upon request.

### SURFACE PRE-TREATMENT

#### Concrete

The concrete shall have a minimum compressive strength of 3500 psi (25 N/mm<sup>2</sup>) and a minimum surface strength of 200 psi (1.4 N/mm<sup>2</sup>) for coatings and 300 psi (2.1 N/mm<sup>2</sup>) for linings. The concrete must be thoroughly cured and dry at the time of application. The residual moisture content should not exceed 4%. ASTM D 4263 plastic sheet test method is recommended to ensure concrete is moisture free. If moisture is detected, repeat test until dry.

Abrasive blast or mechanically abrade surface to remove the weak laitance and surface contaminants. Refer to specification, RCC TT-3 for details.

### APPLICATION

#### Primer:

**COROFLAKE 67PS PRIMER** is recommended when **COROFLOOR EP** is used as an unfilled coating system

and, when required, as a dry\* primer coat for **COROFLOOR EP** broadcast and trowel applied systems. **COROFLOOR EP** resin and hardener mixture is also acceptable for dry priming and is typically used as a wet primer for trowel applied flooring applications.

\* Dry priming is recommended for applications in direct sunlight, on existing or porous concrete floors, or where potential concrete breathing issues exist. Mix and apply primer by roller, brush or spray. Allow it to dry (cure) before applying subsequent coats.

#### Floor Coating System:

- **COROFLOOR EP** is normally applied in two (2) coats at 8-12 mils (200-300 µm) per coat by roller or squeegee and back roll method.

#### Broadcast Floor Coating System:

- Apply catalyzed **COROFLOOR EP Resin** basecoat at 20-24 mils (500-600 µm) by roller or notched squeegee.
- While the resin basecoat is still wet apply 20-40 mesh broadcast aggregate in excess to cover the entire resin surface until no wet areas are evident.
- After the basecoat has cured vacuum or sweep excess aggregate from the flooring surface.
- Mix and apply **COROFLOOR EP** as a topcoat over the exposed aggregate surface at 20-24 mils (500-600 µm) to seal the system. More or less resin can be used to achieve the desired degree of surface texture.
- Thicker and/or multiple broadcast layers can be applied to meet specification requirements.

#### Trowel Applied Flooring:

- Mix and apply **COROFLOOR EP** as a wet primer immediately before placement of the Body Coat.
- Premix **COROFLOOR EP Resin** and **Hardener** and pour mixture into a mortar mixer. Gradually add aggregate at an approximate aggregate to resin mix ratio of 8:1. Mix until the aggregate is thoroughly wetted before discharging from the mixer.
- Apply the Body Coat mixture and trowel to the desired thickness (typically 1/4"). Allow to cure.
- Apply 1 or 2 grout coats of **COROFLOOR EP** as required to seal the system. **COROGARD 66** or **COROFLAKE 611** can also be used as a final grout coat/topcoat.

**Note:** During application the lined surface should be shaded from direct or indirect sunlight when possible.

RCC Corrosion Control	COROFLOOR EP	Revision: 05/31/2022
Replaces all previous editions	Product Data Sheet	Page 1 of 2

## MIX RATIO

Mixing ratio of **COROFLAKE 67PS Resin to Hardener No. 7** is 2:1 by volume. Mixing ratio of **COROFLOOR EP Resin to Hardener No. 9** is 2:1 by volume. Filler and aggregate loading varies with the floor system design type.

## CONSUMPTION

Layer	Thickness mils (µm)	Typical Practical Coverage
PRIMER on concrete <b>COROFLOOR EP:</b> System Design Type:	2-5 (50-125)	160-200 ft <sup>2</sup> /gal
Coating system (per coat)	8-12 (200-300)	120-180 ft <sup>2</sup> /gal
Broadcast Flooring (1/16")	60 (1500)	
Resin Basecoat	20-24 (500-600)	60-72 ft <sup>2</sup> /gal
Broadcast Aggregate	-	1 lb./ft <sup>2</sup>
Topcoat	15-20 (375-500)	72-96 ft <sup>2</sup> /gal
Troweled Flooring (1/4")		
Body & Grout Coat Resin	1/4 in (~ 6 mm)	24-26 ft <sup>2</sup> /gal
Body Coat Aggregate		2 lb/ft <sup>2</sup>

## WORKING TIME & RECOAT TIME

Temperature	Working Time	Min Recoat	Max Recoat
50°F (10°C)	approx. 90 min	16 hrs	14 days
70°F (21°C)	approx. 50 min	8 hrs	14 days
90°F (32°C)	approx. 25 min	4 hrs	7 days

## CURE TIME (to place in service)

Temperature	Minimum Cure time
50°F (10°C)	5 days
70°F (21°C)	3 days
90°F (32°C)	2 days

Technical Data	Testing Standard	Unit	Value
Color			Clear, Grey or Tile Red
Density	ASTM D1475	lbs/gal kg/l	9.32 ± 0.25 1.12
Viscosity – mixed (colored resin)	ASTM D2196	cps (mPa·s)	1000
Adhesion Strength - Concrete	ASTM D7234	Psi (N/mm <sup>2</sup> )	Exceeds concrete strength
Compressive strength (Troweled/filled system)	ASTM C579	Psi (MPa)	9,500-11,500 (66-79)
Tensile Elongation (Binder Only)	ASTM D 638	%	5%
Tensile Strength (Binder Only)	ASTM D638	Psi (MPa)	3000 (21)
Volatile Organic Compounds	EPA Method 24	g/L (lbs/gal)	58 (0.48)
Maximum Operating Temperature*			
Frequent Splash/Spill Concrete		°F °C	140 60
Occasional Splash/Spill Concrete		°F °C	200 93

\*Maximum operating temperature limits may vary depending on actual service conditions

We warrant that our goods will conform to the description contained in the order and that we have good title to all goods sold. This Product Data Sheet is considered accurate and reliable to the best of our knowledge at the date of its publication, but are used as guides only. The user assumes all risks and liabilities in connection therewith regardless of any suggestion, we may give. We assume no liability for performance of the product or for any loss or damage resulting from its use. Our liability, in law and equity, shall be expressly limited to the replacement of non-conforming goods at our factory, or at our sole discretion, to repayment of the purchase price of the non-conforming goods.

Generally **COROFLOOR EP** can be placed into service after the final cure time intervals have been achieved. Shorter or longer intervals may apply depending on service conditions. Consult RCC Corrosion Control for specific recommendations.

**CLEANING:** Cleaning Agent T-100

## SAFETY MEASURES

The material safety data sheets of the individual components as well as the legal requirements for handling hazardous materials must be observed.

## PACKING UNITS

The products are supplied in the following standard package sizes:

Description	Package Size
<b>COROFLAKE 67PS PRIMER</b>	.75, 3, 15, 45 gal kits
<b>COROFLOOR EP</b>	3, 15, 45 gal kits

## STORAGE

The materials must be stored in a cool and dry place. At storage temperature of 70°F (21°C) the shelf life is as follows:

<b>COROFLAKE 67PS PRIMER Resin</b>	24 months
<b>Hardener No. 7</b>	24 months
<b>COROFLOOR EP Resin</b>	24 months
<b>Hardener No. 9</b>	24 months

If the storage time is exceeded, the materials must be tested before use. Higher storage and transport temperatures will reduce the shelf life. The containers must be kept tightly closed. Liquid products must be stored frost-proof.

RCC Corrosion Control	COROFLOOR EP	Revision: 05/31/2022
Replaces all previous editions	Product Data Sheet	Page 2 of 2